



EKOTEKS

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**
Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar
İstanbul/ TÜRKİYE



AB-0583-T

2400009386-
RER

03.25

TEST REPORT
DENEY RAPORU

Report Nr / Revision Nr : 2400009386
Customer name : ALDO BEBEK ÜRÜNLERİ SANAYİ VE TİCARET LTD.ŞTİ
Applicant Address : AKTİM AKÇABURGAZ MH AKBURGAZ CD No:20-AB Esenyurt / ISTANBUL
Buyer name : -
Contact Person : -
Sample Accepted on : 21.11.2024
Re-submitted/re-confirmation date : -
Date of test : 22.11.2024 / 17.12.2024
Fiber Composition : Claimed to be :-
Sample Description : 01 – SILICONE ROUND TEAT ,FİNGER TOOTHBRUSH
02 – BREAST PUMP

Model Number : 460-461-462- Silicone Round Teat :No:1 No:2 No:3
463-464-465- Silicone Orthodontic Teat : No:1 No:2 No:3
480- Fruit Sieve Teat
1001- Silicone Nipple Protector
950- Baby Finger Teeth Brush
1010- Breast Pump

Previous Report No : -

Sampling : The results given in this report belong to the received sample by vendor.
End use : -
Care label : -

Decision Rule : -
Disclaimer Statement : -
Conformity Assessment : -

The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test reports. EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş. accredited by TÜRKAK under registration number [AB-0583-T] for ISO 17025:2017 as test laboratory. The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.

Seal

Date
06.03.2025

Customer Representative
YAGMUR OKUMUS

Laboratory Manager
Sevim A. RAZAK
06.03.2025



This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T
2400009386 -RER
03.25

TEST RESULTS

TEST	METHOD	EVALUATION
DETERMINATION OF PHTHALATES	CPSC-CH-C1001-09.4:2018	P
DETERMINATION OF PAH's	IN HOUSE METOT - EKOTEKS 56 (ISO 16190:2021)	P
DETERMINATION OF BISPHENOLS (*)	Inhouse Method	P
DETERMINATION OF VOLATILE COMPOUNDS (*)	TS EN ISO 4684:2009 (*)	P

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified.If requested, measurement uncertainty will be reported. But unless otherwise specified, measurement uncertainty is not considered while stating compliance with specification or limit values The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95%. The declaration of conformity was given in accordance with the Simple Acceptance Decision Rule. (without considering the level of confidence and measurement uncertainty , evaluation of suitability or non-conformity based on whether the test result obtained is only within the specified limits) Tests marked (*) in this report are not included in the accreditation schedule.

Note: The report dated 17.12.2024 dated 2400009386 has been added to the 2400009386 -RER due to the change of "Customer name" and has been replaced with the report dated 06.03.2025

TEST RESULTS

Photo of the sample received



TEST RESULTS

Photo of the sample received



This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.

AB-0583-T
2400009386 -RER
03.25

TEST RESULTS

Sample ID	Part No.	Part ID	Explanatory Information
A	1	Plastic replacement tips	
A	2	Transparent breast pump	
A	3	feeding bottle teats	
A	4	plastic nipple cap	
A	5	plastic finger brush	

Summary of Results

Parts & Results															
Parts	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15
DETERMINATION OF PHTHALATES	P	P	P	P	P	-	-	-	-	-	-	-	-	-	-
DETERMINATION OF PAH's	P	P	P	P	P	-	-	-	-	-	-	-	-	-	-
DETERMINATION OF BISPHEOLS	P	P	P	P	P	-	-	-	-	-	-	-	-	-	-
DETERMINATION OF VOLATILE COMPOUNDS	NA	NA	NA	-	-	-	-	-	-	-	-	-	-	-	-

P Pass
F Fail
LS Lack of sample.
NA Not applicable
R Refer to retailer technologist

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T
2400009386 -RER
03.25

TEST RESULTS

DETERMINATION OF PHTHALATES

CPSC-CH-C1001-09.4:2018

Test sample is extracted in suitable organic solvent in extraction device. The extract is analyzed by GC-MS and result is given.

Tested Parts	Result (ppm)	Result (%)	Total Results (ppm)	Total Results (%)	Limit Value (ppm)	Limit Value (%)	Extraction Method	Evaluation
3+1+4	N.D	<0.006	< 60	<0.006	Total: 100	Total : 0.1	-	PASS
2+5	N.D	<0.006	< 60	<0.006	Total: 100	Total : 0.1	-	PASS

BBP/ Butylbenzylphthalate (85-68-7) DBP/ Dibutylphthalate (84-74-2)
DEHP/ Di-(2-ethylhexyl) phthalate (117-81-7) DCHP/ Di-cyclohexylphthalate (84-61-7)
DIBP/ Bis - iso -butyl phthalate (84-69-5) DINP/ Di-iso-nonylphthalate (28553-12-0)/ (68515-48-0)
DNHP/ Di-n-hexyl phthalate (84-75-3) DMP/ Dimethylphthalate (131-11-3)
DPP/ Di-pentylphthalate (n-, iso-, or mixed) (131-18-0) / (605-50-5) (776297-69-9) / (84777-06-0)
DEP/ Di-ethylphthalate (84-66-2) DMEP/ Di-(2-methoxyethyl) phthalate (117-82-8)
DIHP/ Di-C6-8-branched alkylphthalates (71888-89-6) DNOP/ Di-n-octylphthalate (117-84-0)
DIDP/ Di-isodecylphthalate (26761-40-0)/ (68515-49-1) DHNUP/Di-C7-11-branched alkylphthalates (68515-42-4)
DHP/ Di-hexylphthalates, branched and linear (68515-50-4)
DIHP/ Di-iso-hexylphthalate (71850-09-4) DIOP/ Di-iso-octylphthalate (27554-26-3)
DPrP/ Di-n-propylphthalate (131-16-8) DNP/ Di-n-nonylphthalate (84-76-4)
1,2-Benzenedicarboxylic acid, di-C6-10 alkyl esters (68515-51-5)
1,2-Benzenedicarboxylic acid, mixed decyl and hexyl and octyl diesters (68648-93-1)

Total Uncertainty:17%

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T
2400009386 -RER
03.25

TEST RESULTS

PAH (POLİ AROMATİK HIDROKARBONLAR)

IN HOUSE METOT - EKOTEKS 56 (ISO 16190:2021)

Tested Parts	Result (ppm)	Total Result (ppm)	Limit Value (ppm)	Evaluation
3+1+4	N.D	< 0.10	<0,5	PASS
2+5	N.D	< 0.10	<0,5	PASS

Naphthalene 91-20-3
Acenaphthylene 208-96-8
Acenaphthene 83-32-9
Fluorene 86-73-7
Phenanthrene 85-01-8
Anthracene 120-12-7
Fluoranthene 206-44-0
Pyrene 129-00-0
1-Methylpyrene 2381-21-7
Benzo(a)anthracene 56-55-3
Cyclopenta(c,d)pyrene 27208-37-3
Chrysene 218-01-9
Benzo(b)fluoranthene 205-99-2
Benzo(k)fluoranthene 207-08-9
Benzo(j)fluoranthene 205-82-3
Benzo(a)pyrene 50-32-8
Benzo(e)pyrene 192-97-2
Indeno(1,2,3-cd)pyrene 193-39-5
Dibenzo(a,h)anthracene 53-70-3
Benzo(g,h,i)perylene 191-24-2
Dibenzo(a,l)pyrene 191-30-0
Dibenzo(a,e)pyrene 192-65-4
Dibenzo(a,i)pyrene 189-55-9
Dibenzo(a,h)pyrene 189-64-0

N.D : Not detected

Total Uncertainty: 12,60%

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T

2400009386
-RER

03.25

TEST RESULTS

DETERMINATION OF BISPHENOLS

Inhouse Method

The results have been determined by the device of Liquid Chromatography - Mass Spectroscopy (LC-MS/MS).

Tested Parts	Result (ppm)	Limit Value (ppm)	Evaluation
3+1+4	< 0.040	0.04	PASS
2+5	< 0.040	0.04	PASS

BISPHENOL A (CAS No : 80-05-7)

VOLATİLE COMPOUND CONTENT; TS EN ISO 4684 :2009 (*)

Place the sample in the oven at (100 ± 5)°C for (60 ± 5) min and (200 ± 5) °C for 4 h ± 5 min.

	WEIGHING RESULT (g)		
Weight A	21,1587		
Weight B	29,0401		
Weight C	29,0265		
Measurement	[(B-C)/(B-A)] X 100		
	<u>RESULT</u>	<u>REQUIREMENT</u>	
	0,2	%0,5 (m/m)	

N.D ⁽¹⁾: Not detected

* W: Withdrawn Method

VOLATİLE COMPOUND CONTENT; TS EN ISO 4684 :2009 (*)

Place the sample in the oven at (100 ± 5)°C for (60 ± 5) min and (200 ± 5) °C for 4 h ± 5 min.

	WEIGHING RESULT (g)		
Weight A	22,1845		
Weight B	32,0347		
Weight C	32,0234		
Measurement	[(B-C)/(B-A)] X 100		
	<u>RESULT</u>	<u>REQUIREMENT</u>	
	0,1	%0,5 (m/m)	

N.D ⁽¹⁾: Not detected

* W: Withdrawn Method